






Technical Data sheet

FieldTurf Tarkett™
UNITED IN SPORT™



Multiflex M

Indoor sports flooring with area deformation

Properties	Standards	Multiflex M
Sports properties		
Friction	EN 13036-4	106
Shock absorption	EN 14 808	52 %
Vertical deformation	EN 14 809	2,3 mm
Vertical ball rebound	EN 12235	98,3 %
Specular gloss	EN 13 747	17%
Classification		
Reaction to fire	EN 13501-1	Dfl-S1 (varnished) Cfl-S1 (unvarnished)
Formaldehyde	EN 717-1 EN 717-2	E1
Pentachlorophenol	EN 12673	No Pentachlorophenol
Technical Characteristics		
Wear layer	EN429	3,6 mm
Abrasion	EN ISO 5470-1	0,06 g
Resistance to indentation	EN 1516	0,07 mm
Behaviour under a rolling load	EN 1569	0,1 mm No degradation
Resistance to impact	EN 1517	No degradation
Specific Characteristics		
Surface treatment	 High strength Proteco® (varnish) or unvarnished upon request.	
Maintenance (see instructions)		
Tree species and available classifications	 Oak (Varnished/Unvarnished)  Beech (Varnished/Unvarnished)	

Key points



Sabanci University - Turkey

Description :

Polyethylene film vapor barrier.
Tarfoam 1500 PU Foam.
Floating plywood sub-floor with a multilayer floor on top-layer, composed of a 3.6 mm hard-wood wear layer (3 pieces per batten) glued on offset wood lathing.

Type of installation :

Multilayer click system glued on plywood and resilient subconstruction. The all system is floating

Destination :

Indoor sports flooring with area deformation.

Installation instructions and maintenance guide :

On request.

Packing dimensions :

- Solid boards : 6 slats/pack, 36 packs/pallet.
- Tarflex 9 mm : 8 slats/pack, 33 packs/pallet.
- Tarfilm : delivered in rolls 159 m².
- Tarfoam 1500 : delivered in rolls 51,75 m².
- Skirting : 6 slats/pack (if ordered).
- Floor-lids and glue gun per unit (if ordered).
- Cardboard of glue (if ordered).

Dimensions (EN 426/EN 427):



188 mm 2 525 mm

Total thickness (EN 428):



38 mm (± 2 mm)

Total weight (EN 430) :









16,10 kg (± 100 g)



Compatible slabs: Concrete, hot-applied asphalt and asphalt screed, anhydrite screed.

Any deviation of the slab must be corrected prior installation (3 mm under a 2 m straight edge). See installation instruction.

We reserve the right to modify these specifications without, however, affecting their compliance with standards

	EN 14904 : 2006 Indoor sport flooring. Floating plywood sub-floor and foam combined with a multiply top-layer.	Fieldturf Tarkett SAS 2 rue de l'Égalité 92748 NANTERRE CEDEX FRANCE
	    	EN 13489 Multiflex M

FIELDTURF TARKETT SAS

2, rue de l'Égalité,
92748 Nanterre Cedex France
Tél. 33 (0)1 41 20 40 40
Fax. 33 (0)1 41 20 47 18/19
<http://www.fieldturfarkett.com>

